

SARDEGNA_20 S3 SRC



DESCRIERE	NORMA EN ISO 20345:2011	REZULTAT	CERINTE NORMA
FETE: Piele naturala neteda de bovina, hidrofobizata, cu element reflectorizant,	5.4.3 Rezistenta la sfasiere ansamblu superior 5.4.6 Permeabilitatea la vapori de apa Coeficient de vapori de apa	207 N 1,2 mg/cm ² h 18,8 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa si caramba Material textil perforat rezistent la abraziune , asigura aerisirea piciorului, antibacterian:	5.5.1 Rezistenta la sfasiere captuseala 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune(mediu uscat 5.5.3 Permeabilitatea la vapori de apa Coeficient de vapori de apa	30 N Fara perforatii Fara perforatii 8 mg/cm ² h 64 mg/cm ²	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Captuseala stail: Material textil perforat rezistent la abraziune , asigura aerisirea piciorului,	5.5.1 Rezistenta la sfasiere captuseala 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune(mediu uscat 5.5.3 Permeabilitatea la vapori de apa Coeficient de vapori de apa	25 N No fori No fori 11,3 mg/cm ² h 90,6 mg/cm ²	≥ 15 N 51.200 cicluri 25.600 cicluri ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Bombeu: Non-metallic <u>din material compozit, rezistent la soc 200J si compresiune</u>	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezisrtenta la compresiune	14,0 mm 14,0 mm	≥ 14 mm ≥ 14 mm
Lamela antiperforare: Material kevlar, perforatie zero	5.7.1. Grosime 5.7.3 Absorbtiia de apa	3,5 mm 72 mg/cm ²	≥ 2,0 mm ≥70,0 mg/cm ²
Acoperis de brant: Tesut preformat pe suport poliuretanic, antistatic, forma anatomica , prevazut cu perforatii, detasabil.	5.7.4.2 Rezistenta la abraziune(mediu umed) Rezistenta la abraziune(mediu uscat)	Fara perforatii Fara perforatii	25.600 cicluri 12.800 cicluri

Talpa: poliuretan dubla densitate, bicolora, antistatica, antiderapanta, rezistenta la abraziune si hidrocarburi. Tip talpa Advanced	5.8.2 Rezistenta la sfasiere	8,3 kN/m	$\geq 8 \text{ kN/m} \leq$
	5.8.3 Rezistenta la abraziune	85 mm ₃	150 mm ₃ $\leq$
	5.8.4 Rezistenta la flexionare	2,00 mm	4,0 mm
	5.8.5 Hidroliza	3,00 mm	$\leq 6,0 \text{ mm}$
	6.4.2 Rezistenta la uleiuri	1%	$\leq 12\%$
	5.11 Rezistenta la alunecare pe placi ceramice acoperite cu detergent		
	Alunecare pe suprafata totala talpa	0,33	$\geq 0,32$
	Alunecare pe calcai	0,29	$\geq 0,28$
	Rezistenta la alunecare pe placi din otel acoperite cu glicerina		
	Alunecare pe suprafata totala talpa	0,21	$\geq 0,18$
	Alunecare pe calcai	0,16	$\geq 0,13$

MARIMI : 35-48; MONDOPOINT 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519
 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207 www.exena.it –
 info@exena.it - pec: amministrazione@pec.exena.it

SARDEGNA 20 S3 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Genuine leather,	5.4.3 Tear strength	207 N	≥120 N
	5.4.6 Water vapor permeability	1,2 mg/cm ² h	≥ 0,8 mg/cm ² h
	Coefficient	18,8 mg/cm ²	≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	30 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No fori	25.600 cycles
	Abrasion resistance(Dry)	No fori	12.800 cycles
	5.5.3 Water vapor permeability	8 mg/cm ² h	≥ 2,0 mg/cm ² h
	Coefficient	64 mg/cm ²	≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	25 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No fori	51.200 cycles
	Abrasion resistance(Dry)	No fori	25.600 cycles
	5.5.3 Water vapor permeability	11,3 mg/cm ² h	≥ 2,0 mg/cm ² h
	Coefficient	90,6 mg/cm ²	≥20,0 mg/cm ²
SAFETY TOE CAP:	5.3.2.3 Impact resistance	14,0 mm	≥ 14 mm
Non-metallic polycarbonate safety toe.	5.3.2.4 Compression resistance	14,0 mm	≥ 14 mm
PIERCE-RESISTANCE: Textile	5.7.1. Thickness	3,5 mm	≥ 2,0 mm
pierce proof footbed,	5.7.3 Water absorption	72 mg/cm ²	≥70,0 mg/cm ²
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles
	Abrasion resistance(Dry)	No holes	12.800 cycles
OUTSOLE: PU 2D, Antislip sole, SRC	5.8.2 Tear strength	8,3 kN/m	≥ 8 kN/m
	5.8.3 Abrasion resistance	85 mm ³	≤ 150 mm ³
	5.8.4 Flexing resistance	2,00 mm	≤ 4,0 mm
	5.8.5 Hydrolysis	3,00 mm	≤ 6,0 mm
	6.4.2 Oils resistance	1%	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,33	≥ 0,32
	Heel slip	0,29	≥ 0,28
	Stainless steel plate on glycerin resistance		
	Flat slip	0,21	≥ 0,18
	Heel slip	0,16	≥ 0,13

SIZES : 35-48; MONDOPOINT 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it

Traducere din limba engleza - in conformitate cu documentul

EXENA

DECLARATIE DE CONFORMITATE UE

M22 -Ver. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, Exena srl DECLARA ca echipamentul individual de protectie di lotul corespunzator de productie descris mai jos:

Articol: **SARDEGNA_20**

Lot: 64171



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S3 SRC

Nr. certificat: F-130-03279-20

Data: **30/03/2020**

EMIS DE: CIMAC – 0465

Civitanova Marche, **20/05/20**

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche Semnatura ilizibila

Sfârșitul traducerii

Traducător autorizat,

Subsemnata **MIHAELA CARMEN LECA**, traducator si interpret autorizat de Ministerul Justitiei cu nr. 14606/07.11.2018 pentru LIMBA ENGLEZA, certific exactitatea acestei traduceri efectuata de mine la cererea partii, conform textului autentic, vizat de mine. Traducatorul nu isi asuma responsabilitatea pentru continutul acestui document.

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item

SARDEGNA_20

batch:

64171



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S3 SRC

certificate numb.:

F-130-03279-20

date:

30/03/2020

issued by:

CIMAC - 0465

Civitanova Marche

20/05/20

EXENA S.r.l.
Via Breda, 7/A - Zona Ind.le A
Tel. 0733 897256 Fax 0733 897519
62012 CIVITANOVA MARCHE - MC
P. IVA 01336080435
CEO

EXENA S.r.l.

Via Breda, 7 - Z.na Ind. A 62012 - CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it - info@exena.it - pec: amministrazione@pec.exena.it