

SUMATRA_20 S3 SRC



DESCRIERE	NORMA EN ISO 20345:2011	REZULTAT	CERINTE NORMA
Fete: Piele intoarsa, cu tratament rezistent la apa	5.4.3 Rezistenta la sfasiere 5.4.6 Coeficient de Permeabilitatea la vapori de apa	174 N 3,1 mg/cm ² h 32,9 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa : cu aerisire si rezistenta la abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Coeficient de Permeabilitatea la vapori de apa	25 N Fara decupaj Fara decupaj 7,7 mg/cm ² 62,0 mg/cm ²	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥ 20,0 mg/cm ²
Captuseala stailf: cu aerisire si rezistenta la abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat) 5.5.3 Coeficient de Permeabilitatea la vapori de apa	25 N Fara decupaj Fara decupaj 7,7 mg/cm ² 62 mg/cm ²	≥ 15 N 25.600 cicluri 12.800 cicluri ≥ 2,0 mg/cm ² ≥ 20,0 mg/cm ²
Bombeau de siguranta: Material compozit nemetalic	5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	14,0 mm 14,0 mm	≥ 14 mm ≥ 14 mm
Lamela antiperforare: Lamelă antiperforație	5.7.1 Grosime 5.7.3 Absorbția de apa	3,5 mm 72 mg/cm ²	≥ 2,0 mm ≥ 70,0 mg/cm ²

nemetalică, perforație zero			
Acoperis de brant: Talpa interioara detasabila, captusita, antistatica	5.7.4.2 Rezistenta la abraziune (mediu umed) Rezistenta la abraziune (mediu uscat)	Fara perforatii Fara perforatii	25.600 cicluri 12.800 cicluri
Talpa: PU 2D, talpa aderenta, SRC	5.8.2 Rezistenta la sfasiere 5.8.3 Rezistenta la abraziune 5.8.4 Rezistenta la flexare 5.8.5.Hidroliză 6.4.2 Rezistenta la uleiuri 5.11 Rezistenta la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii Alunecare pe calcai Rezistenta la alunecare pe placi din otel acoperite cu glicerina Alunecare pe suprafata totala a talpii Alunecare pe calcai	8,3 kN/m 85 mm ³ 2,0 mm 3,0 mm 1.0% 0,33 0,29 0,21 0,18	≥ 8 kN/m ≤ 150mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

MARIMI : 35-48 MONDOPOINT 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519 C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207 www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

SUMATRA 20 S3 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Genuine leather, water repellent treatment, breathable textile	5.4.3 Tear strength 5.4.6 Water vapor permeability Coefficient	174 N 3,1 mg/cm ² h 32,9 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength 5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry) 5.5.3 Water vapor permeability Coefficient	25 N No holes No holes 7,7mg/cm ² h 62,0 mg/cm ²	≥ 15 N 25.600 cycles 12.800 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
QUARTER LINING: Breathable, abrasion resistance.	5.5.1 Tear strength 5.5.2 Abrasion resistance(Wet) Abrasion resistance(Dry) 5.5.3 Water vapor permeability Coefficient	25 N No holes No holes 7,7 mg/cm ² h 62,0 mg/cm ²	≥ 15 N 51.200 cycles 25.600 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
SAFETY TOE CAP: Non-metallic polycarbonate safety toe.	5.3.2.3 Impact resistance 5.3.2.4 Compression resistance	14,0 mm 14,0 mm	≥ 14 mm ≥ 14 mm
PIERCE-RESISTANCE: Textile pierce proof footbed,	5.7.1. Thickness 5.7.3 Water absorption	3,5 mm 72 mg/cm ²	≥ 2,0 mm ≥70,0 mg/cm ²
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance(Wet) Abrasion resistance(Dry)	No holes No holes	25.600 cycles 12.800 cycles
OUTSOLE: PU 2D, Antislip sole, SRC	5.8.2 Tear strength 5.8.3 Abrasion resistance 5.8.4 Flexing resistance 5.8.5 Hydrolysis 6.4.2 Oils resistance 5.11 Pressed ceramic tile floor on detergent resistance Flat slip Heel slip Stainless steel plate on glycerin resistance Flat slip Heel slip	8,3 kN/m 85 mm ³ 2,00 mm 3,00 mm 1% 0,33 0,29 0,21 0,16	≥ 8 kN/m ≤ 150 mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

SIZES: 35-48; MONDOPOINT: 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it

Traducere din limba engleza - in conformitate cu documentul

EXENA

DECLARATIE DE CONFORMITATE UE

M22 -Ver. 00

Conform regulamentului (UE) 2016/425 – Anexa IX, **Exena srl** DECLARA
ca echipamentul individual de protectie si lotul respectiv de productie
descrie mai jos:

Articol: **SUMATRA_20**

Lot: **63534**



Este in conformitate cu standardul: EN ISO 20345:2011

Clasa: II

Categoria de marcaj: S3 SRC

Nr. certificat: F-130-03276-20

Data: **30/03/2020**

EMIS DE: CIMAC – 0465

Civitanova Marche, **21/05/20**

Aplicata parafa firmei EXENA S.R.L.

Sediul in Via Breda, 7/A

Civitanova Marche, Semnatura ilizibila

Sfârșitul traducerii

Traducător autorizat,

Subsemnata **MIHAELA CARMEN LECA**, traducator si interpret autorizat de
Ministerul Justitiei cu nr. 14606/07.11.2018 pentru LIMBA ENGLEZA, certific
exactitatea acestei traduceri efectuata de mine la cererea partii, conform textului
autentic, vizat de mine. Traducatorul nu isi asuma responsabilitatea pentru
continutul acestui document.

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item

SUMATRA_20

batch:

63534



conforms to the standard:

EN ISO 20345:2011

class:

II

marking category:

S3 SRC

certificate numb.:

F-130-03275-20

date:

30/03/2020

issued by:

CIMAC - 0465

Civitanova Marche

21/05/20

EXENA S.r.l.
Via Breda, 7/A - Zona Ind.le A
Tel. 0733 897256 Fax 0733 897519
62012 CIVITANOVA MARCHE - MC
P. IVA 01336080435
CEO

EXENA S.r.l.

Via Breda, 7 - Z.na Ind. A 62012 - CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it - info@exena.it - pec: amministrazione@pec.exena.it